UNCLASSIFIED

AD NUMBER

AD499509

CLASSIFICATION CHANGES

TO: unclassified

FROM: confidential

LIMITATION CHANGES

TO:

Approved for public release, distribution unlimited

FROM:

Distribution authorized to DoD only; Administrative/Operational Use; 07 APR 1952. Other requests shall be referred to Naval Proving Ground, Dahlgren, VA. Pre-dates formal DoD distribution statements. Treat as DoD only.

AUTHORITY

USNSWC ltr dtd 14 Aug 1975; USNSWC ltr dtd 14 Aug 1975

THIS REPORT HAS BEEN DELIMITED AND CLEARED FOR PUBLIC RELEASE UNDER DOD DIRECTIVE 5200.20 AND NO RESTRICTIONS ARE IMPOSED UPON ITS USE AND DISCLOSURE.

and the state of t

DISTRIBUTION STATEMENT A

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED. U. S. HAVAL PROVING GROUND DAHLGREN, VIRGINIA

REPORT NO 956

WARHEADS FOR AIR TARGET GUIDED MISSILES; TESTING OF

41st Partial Report

INVESTMENT CAST STEEL TUBE FOR AIR TARGET GUIDED MISSILES: FRAGMENTATION TEST OF

Assignment NPG-Re3f-607-1-52

Classification

Task

FINAL Report

N. P. C.

Clarific Commence

U. S. NAVAL PROVING GROUND DAHLGREN, VIRGINIA

STERENCE DEPARTMENT

22195

Forty-first Partial Report

on

Warheads for Air Target Guided Missiles; Testing of

Final Report


orı


Investment Cast Steel Tube for Air
Target Guided Missiles; Fragmentation Test of

Project No.: NPG-Re3f-607-1-52 Copy No.: 13 No. of Pages: 7

Date: APR & 100%

COMMUNICATION OF THE SECOND OF





· ! NP9-46934

4 DECEMBER 1951

CONFIDENTIAL SECURITY INFORMATION


Mass Distribution of 4.6 dismeter, 0.45 wall thickness, and 9.25 long.
Investment Cast Steel Tube Warhead, Composition C-3 loaded.
Figure 2

TABLE I

MASS DISTRIBUTION DATA

		Photo	40 ·	NP9	46934	
STEEL TUBE WARHEAD: 4"6 0.D.; "45 WALL, 9"25 LONG, COMP C-3 LOADED SELASTING CAP AND TETRYL 300STER FROM MK 44 AUX. DET.			- 装	٥	6624 1276	
#25 LONG, C	40-80	Grams	Wt.	Gms. No.	330 7	
STEEL TUBE WARHEAD: 4"6 0.D.; "45 WALL, 9"25 LON BLASTING CAP AND TETRYL 300STER FROW WK 44 AUX. 12GFENTS	20-40	Grams	ut.	Gms. No.	1582 57	
4"6 O.D.; PRYL 300STE	10-20	Grams	34C.	Gms. No.	1506 124	
CAP AND TE	5-10	urams	//t.	Gms No.	1185 174	
f Steel tuei RS Blasting Fraghents	2 .5-5	CI chills	٠ ۲ <u>٠</u>	Gms No.	732 217	
SSTPENT CAST IAL ENGINEED RECOVERED T	1.25-2.5	TITE COMES	٠. د د د	Gms No.	596 341	
FRACMENTATION OF INVESTMENT CAST FUZE: SPECIAL ENGINEERS NUMBER AND WEIGHT OF RECOVERED FR	5/8-1.25 Grams	174	- 1 - 1 - 1	Sms No.	308 356	
FRAGRENTATION OF FUZE: S NUPBER AND WEIGHT	0-5/8 Grams	104	• o a c	Gills NO	385	
	Filler	WH	· 4	10.	5,63	
	Comp.	Wt.	, 4.		20.48	
		Rd	NO		H	

PPENDIX B



The state of the s

Investment Cast Steel Tube for Air Target Guided Missiles; Fragmentation Test of

DISTRIBUTION

Bureau of Ordnance:	
Ad3 Re2 Re3 Re3f	1 2 5
Chief of Ordnance Department of the Army Attn: ORDTX-AR	2
Navy Research Section Library of Congress Washington 25, D. C. (Via BUORD Re3)	2
Commanding General Aberdeen Proving Ground Aberdeen, Maryland Attn: Technical Information Section Development and Proof Services	1
Commander, Operational Development Force U. S. Atlantic Fleet, U. S. Naval Base	


1 Norfolk 11, Virginia 1 Naval Ordnance Laboratory Naval Ordnance Laboratory Attn: Explosives Division 1 Attn: Mr. H. W. Semon 1

Picatinny Arsonal, Dover, N. J. Attn: Technical Division Reports Office APL/JLU, Silver Spring, Maryland 1

APL/JhU, Silver Spring, Md. Attn: Mr. H. S. Morton (Via INSORD, Silver Spring, Md.) 1



1




APPENDIX C



DISTRIBUTION (Continued)

Bureau of Ordnance Technical Liaison Office	
naia malannone babbi water	1
Whippany, New Jersey	1
USNOTS, Invokern, China Lake, Calif.	
Inst. for Cooperative Research JHU/1315 St. Paul St. Via: (District Chief, Phila. Ord District Via: 1500 Chestnut St., Phila. 2, Pa. Attn: Mr. Edward R. C. Niles)	1
Director, Research and Development Division New Mexico Institute of Mining and Technology New Mexico	
New Mexico Socorro, New Mexico Via: Development Contract Officer Via: Development Contract Officer New Mexico Institute of Mining and Technology Socorro, New Mexico	1
Boeing Airplane Company Seattle Division Seattle, Washington	1
Local:	1
OT OTZ OT-1 File	1 1 1 1





En Ca


NPG REPORT NO. 956

Investment Cast Steel Tube for Air Target Guided Missiles; Fragmentation Test of

PART A

SYNOPSIS

- 1. This test was conducted to determine the fragment mass distribution of a Composition C-3 loaded investment cast steel tube.
- 2. a. Approximately 70% of the total weight of the warhead fragmented into fragments weighing more than 5 grams each.
- b. The fragment mass distribution compared favorably with that obtained from similar steel tubes manufactured by other processes.




· · · cerrons or before a benefit to be a service of the service o

Investment Cast Steel Tube for Air Target Guided Missiles; Fragmentation Test of

TABLE OF CONTENTS

																											Page
SYNOP	SIS	•		•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	1
Table	OF	С	01	T	EN	TS	i .	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	2
AUTHO	RIT	Υ.		•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	3
REFER	INC	ES		•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•		•	•	•	•	•	•	3
BACKGI	ROU	ND)	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	3
OBJEC!	r o	F	TI	E۵	T	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	3
PERIO	D 0	F	T	ES	T	٠	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	3
DESCR.	IPT	IO	N	0	F	IT	EM	ับ	ND	ER	1	'ES	T	•	•	•	•	•	•	•	•	٠	•	•	•	•	4
PROCE	DUR	E.		•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	5
RESUL!	rs	ΛN	D	D	IS	CU	ဌန	IO	N	•	•	٠	•	•	•	•	•	•	•	•	•	٠	•	•	•	•	5
CONCL	JSI	ON	S	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	6
APPEN	DIX	. A		-	W.A	RE	Ľr.	.D,	P	ΉC	TC	GR	AF	H		•	•	•	•	•	•	•	F	GŪ	JR E	E 1	L
APPENI	XIO	B	; .	-	MA	.SE	5 D	IS	TR	ΙE	UI	`IC	N	DA	ΑTA	•	•	•	•	•	•	٠				e 2 1	_
APPENI	DΙλ	C	; .	_	DI	ST	RI	ВU	ΤI	ON	i.	÷			•	•	•	•		•	•	•	1-	-2	()	Inc	21)



PART B

INTRODUCTION

1. AUTHORITY:

This test was authorized by reference (a) and conducted under Task Assignment NPG-Re3f-607-1-52, reference (b).

REFERENCES:

- a. BUORD Conf ltr NP9 Re3f-EJHL:edb Ser 12896 of 26 Sep 1951 b. BUORD Conf ltr NP9 Re3f-EJHL:edb Ser 25777 of 18 Sep 1951 c. NPG Conf Report No. 705 of 16 Jan 1951 d. NPG Conf Report No. 681 of 15 Nov 1950

3. BACKGROUND:

THE PROPERTY OF THE PROPERTY O

In the development of varhead cases for air target guided missiles, an investment cast steel tube was manufactured. The casting of steel tubes is a simple and expeditious method of manufacturing warhead cases.

OBJECT OF TEST:

This test was conducted to determine the fragment mass distribution of a Composition C-3 loaded investment cast steel tube.

5. PERIOD OF TEST:

- b. Date Project Letter
 b. Date Necessary Material Received
 c. Date Commenced Test
 d. Test Completed

- 26 September 1951
- 24 September 1951
- 4 December 1951
- 4 December 1951

PART C

DETAILS OF TEST

6. DESCRIPTION OF ITEM UNDER TEST:

From an investment cast steel tube, cylindrical, 4"6 outside diameter, "45 wall thickness, 9"25 long, manufactured by S. D. Hicks and Son Co., a 2 1/2" x 2 1/2" section from one end was removed for physical tests. The physical properties and chemical analysis of this tube were as follows:

Physical Properties: (Tests conducted at NPG)

Test No.	Yield Strength at 0.2% offset (psi)	Tensile Strength (psi)	Elongation (% in 4d)	Reduction of Area (%)
1 2 3	28,000 24,000 22,500	35,800 33,100 32,400	2.7 2.7 4.0	5.4 6.5 10.4
Average	24,800	33,800	3.1	7.4

Chemical Properties: (reported in reference (a))

<u>C</u>	<u>Si</u>	<u>Mn</u>
.10	•39	.69

The warhead was loaded with Composition C-3, and the veights wer: as follows:

Enpty	Comp. $C-3$	<u>Total</u>			
14.85 lbs.	5.63 lbs.	20.48 lbs.			

7. PROCEDURE:

ALTERATION OF THE CONTRACT OF

The warhead was initiated by a MK 44 auxiliary detonating fuze tetryl pellet and a special engineers blasting cap in a sawdust-filled chamber. After the detonation, the sawdust was sifted and the fragments recovered by the use of sieves and a magnetic separator.

8. RESULTS AND DISCUSSION:

The detailed mass distribution data are listed in Table I and the fragments are shown in Figure 2. The number of fragments in the various weight groups are summarized as follows:

Wt. Group	No.	Wt. of Fragments (gm.)	% of Total
(grams)	<u>Fragments</u>		Weight
40-80 20-40 10-20 5-10 2 1/2 - 5 1 1/4 - 2 1/2 5/8 - 1 1/4 0 - 5/8	7 57 124 174 217 341 356	330 1582 1506 1185 732 596 308 385	5 24 23 18 11 9 4

Approximately 70% of the total warhead weight fragmented into fragments which were greater than 5 grams in weight. Comparing the fragment sizes with those recovered from similar size warheads manufactured by processes other than casting, references (c) and (d), indicate that the casting of cases may be a satisfactory method for producing warheads. It should be noted, however, that the results reported in references (c) and (d) are for warheads with substantially thinner walls, so that no exact comparison can be made.




PART D

CONCLUCIONS

- 9. a. Approximately 70% of the total weight of the warhead fragmented into fragments weighing more than 5 grams each.
- b. The fragment mass distribution compared favorably with that obtained from similar steel tubes manufactured by other processes.







The tests upon which this report is based were conducted by: V. PHILIPCHUK, Fragmentation Battery Officer, Fragmentation Division,

Terminal Ballistics Department

H. E. ROMINE, Head, Metallurgy Division, Terminal Ballistics Department

This report was prepared by:
V. PHILIPCHUK, Fragmentation Battery Officer,
Fragmentation Division,
Terminal Ballistics Department

This report was reviewed by:

R. F. LYDDANE, Director of Research Terminal Ballistics Department

W. B. ROBERTSON, Lieutenant Commander, USN
Terminal Eallistics Batteries Officer
Terminal Ballistics Department

R. T. RUBLE, Lieutenant Commander, USN
Terminal Ballistics Officer
Terminal Ballistics Department

C. C. BRAMBLE, Director of Research, Ordnance Group

APPROVED: IRVING T. DUKE
Rear Admiral, USN
Commander, Naval Proving Ground

C. T. MAURO
Captain, USN
Ordnance Officer
By direction

